



NIPPON PAINT

Hydro Block 2K

Waterproofing Coating

Walltron Hydroblock 2K is a two-component cementitious, flexible waterproofing coating. It is composed of best quality portland cement, properly selected and graded aggregates, additives & Acrylic polymer as a binder. It is applied to waterproof and protect concrete structures.

GREEN ASSURED



PRODUCT FEATURES



Flexibility

Provides a flexible & low permeable coating



Waterproof

Waterproofing of concrete structures



Adhesion

Provides an elastic film with excellent bonding with cementitious substrates



Crack Bridging

Can bridge cracks up to 1 mm



Efflorescence Resistant

Provides protection against efflorescence



Anti Carbonation

Prevents carbonation of concrete



Seamless Coat

Forms a seamless coating



Application

Easy to apply

APPLICATION AREA:

Suitable for use on new & old concrete/mortar/plaster surface which is in good condition.

Specially designed for Waterproofing of:

- Bathrooms, toilets, balconies, water tanks, basements & retaining walls
- Waterproof coating (bottom coat) for marble, granite and other natural stones
- Masonry surface: Brick walls/concrete slabs subjected to damage from moisture/efflorescence





**NIPPON
PAINT**

Hydro Block 2K
Waterproofing Coating

TECHNICAL DETAILS

Mix ratio (Powder : Liquid), by weight		2:1
Surface Dry time, minutes	ASTM D 1640	40 - 50 mins
Recoatibility time, Hrs		4 - 6
Elongation at break, %	ASTM D 412	75 %
Adhesion strength, MPa	ASTM D 4541	0.7

Coverage:



WALLTRON HYDROBLOCK 2K

0.70 - 0.74 sq ft/kg/2 coats

Coverage can vary depending upon the nature of the substrate.

HOW TO APPLY

Surface Preparation:



- The surface must be strong & free from dirt, dust & loose particles.
- Thoroughly wire brush the surface & clean the dust by air compressor or wash the surface with water. Oil & grease must be removed using degreasing solvents.
- Any damaged surface must be repaired by using a suitable Walltron product.
- In case of efflorescence, cement plaster should be removed well over and wider of the affected area up till the brick level.
- Prior to application the surface must be in Saturated Surface Dry (SSD) condition.

Mixing

- Shake the liquid component well.
- Transfer entire quantity of liquid component into a suitable clean mixing vessel, gradually start addition of powder component under constant mixing.
- In case of large quantity use mechanical stirrer.
- Mix the entire quantity until a smooth homogeneous slurry without lump is achieved.

Application:

- Apply Walltron Hydroblock 2K slurry by brush over SSD masonry/brick surface.
- Allow the surface to dry for 4-6 hours. Drying will depend on temperature & humidity. Then apply second coat in perpendicular direction to the first coat.
- Ensure a forced coverage of 15 - 17 sq.ft./kg/coat.
- Ensure overlay of cementitious screed / plaster within 24 to 48 hrs.
- In case of fresh concrete/masonry substrate - the surface must be cured for 28 days before application.

Precautions and Limitations:

- Mix the entire quantity of both the components.
- Always add powder to liquid, to ensure the mixture is free of lumps.
- Do not add water during mixing/application.
- Do not use powder with any other the liquid, it will affect the performance.
- Do not flood the treated surface with water until it is completely cured.

SAFETY AND ENVIRONMENT

During Painting:

Always work in well ventilated area. Wear appropriate attire, especially gloves and eye protection, mask. Avoid contact with skin as it may cause irritation.

Cleaning:

Wash all tools with clean water immediately after application.

Safety Instructions:

In case of eye contact rinse immediately with water and seek immediate medical treatment. To remove the material from skin, use soap and water or appropriate cleanser. Safety datasheets will be made available to professional users upon request

Storage:

Store in a cool dry and well ventilated place away from heat sources, flammables or direct sun light. Do not store near food, drinks or animal feed. Keep out of reach of children.

Shelf Life:

Best before 6 months from date of manufacturing in unopened original packing when stored in dry condition.

Disclaimer:

The information contained in this Technical Data Sheet is based on laboratory tests and practical experience and is provided in good faith to the best of our current knowledge. However, no warranty, express or implied, is given regarding the accuracy, reliability, or completeness of this information. Due to the variety of materials, substrates, site conditions, and methods of application beyond our control, the company expressly disclaims any liability for loss or damage resulting from improper use of the product or reliance on the information provided herein. It is the responsibility of the customer or end user to ensure the product's suitability and compatibility for the intended application by conducting appropriate testing or sampling. For specific recommendations or further technical support, please consult our technical representatives.

